

## Biresin® LS Laminating and Multi-purpose resin

### Areas of Application

- Manufacture of true-to-size, mechanical resistant laminates with glass or carbon fibres
- Manufacture of laminated foam and compression moulds
- Backstampings of moulds, models, negatives and tools
- Also used for coupling layers

### Product Benefits

- Multi-purpose application with different hardeners
- Good soaking and wetting properties
- For high addition of fillers
- With **Biresin® F4 (B)** for longer potlife and lower viscosity
- With **Biresin® S10 (B)** for shorter potlife and thinner layers
- Additional hardeners: see separate leaflet

### Description

- Basis Two component epoxy system
- Component A **Biresin® LS**, epoxy resin, yellowish-transparent, unfilled
- Component B **Biresin® LS**, standard hardener, amine, colourless-transparent, unfilled
- Component B **Biresin® F4**, amine, colourless, unfilled
- Component B **Biresin® S10**, amine, amber, unfilled

Processing Data		Component A		Component B	
Individual components		Biresin® LS	Biresin® LS	Biresin® F4	Biresin® S10
Viscosity, 23°C	mPa.s	~ 1,250	~ 40	< 10	~ 3,500
Density, 25°C	g/ml	1.14	0.98	0.87	1.05
Mixing ratio A : B	in pbw	100	12	18	22
<b>Mixtures</b>					
Mixed viscosity, 23°C	mPa.s	~ 580		~ 350	~ 3,500
Potlife, 500 g, RT	min	55		80	10
Demoulding time, RT	h	12		16	8

### Physical Data (approx. values)

Biresin® LS (A) with component B			Biresin® LS		Biresin® F4		Biresin® S10	
Density	ISO 1183	g/cm³	1.2		1.2		1.2	
Curing conditions	time	temperature	14 d RT	2 h 80°C	14 d RT	2 h 80°C	14 d RT	2 h 80°C
Shore hardness	ISO 868	-	D 83	D 83	D 80	D 82	D 83	D 84
E-Modulus	ISO 178	MPa	2,420	2,630	2,440	2,570	2,900	2,900
Flexural strength	ISO 178	MPa	95	107	88	94	108	117
Compressive strength	ISO 604	MPa	104	106	91	94	110	112
Tensile strength	ISO 527	MPa	69	74	67	69	69	74
Impact resistance	ISO 179	kJ/m²	10	14	18	44	16	21
Heat distortion temperature	ISO 75B	°C	51	70	46	53	53	82

### Packaging

Individual components	<b>Biresin® LS (A)</b>	220 kg; 50 kg; 20 kg net
	<b>Biresin® LS (B)</b>	2.4 kg net
	<b>Biresin® F4 (B)</b>	2.5 kg net
	<b>Biresin® S10 (B)</b>	2.5 kg net

## Processing

- The material, processing and mould temperature must be from 18 to 25°C.
- After mixing the two components it is easily possible to incorporate additives if necessary.
- Biresin® LS is applied quickly and easily due to its low viscosity. It will easily wet out fibres and incorporate high levels of fillers and powders with high binding force.
- The ratio between resin and selected fibre must be determined and reliably controlled.
- For laminates glass fibres with binding twill are better than binding cloth because of its better suppleness.
- It is advised to lay up a balanced laminate to avoid distortion when de-moulding.
- Void-free glass and carbon fibre laminates are possible by processing under vacuum bag conditions to remove excess air and resin.
- To clean brushes or tools immediately Sika® Reinigungsmittel 5 is recommended.

## Storage

- Minimum shelf life is 24 month under room condition (18 - 25°C), when stored in original un-opened containers.
- After prolonged storage at low temperature, crystallisation of components may occur. This is easily removed by warming up for a sufficient time to a maximum of 80°C. Allow to cool to room temperature before use.
- Containers must be closed tightly immediately after use to prevent moisture ingress. The residual material needs to be used up as soon as possible

## Health and Safety Information

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety related data.

## Disposal considerations

Product Recommendations: Must be disposed of in a special waste disposal unit in accordance with the corresponding regulations.

Packaging Recommendations: Completely emptied packagings can be given for recycling. Packaging that cannot be cleaned should be disposed of as product waste.

## Value Bases

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## Legal Notice

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Further information available at:

Sika Deutschland GmbH

Subsidiary Bad Urach

Stuttgarter Str. 139

D - 72574 Bad Urach

Germany

Tel: +49 (0) 7125 940 492

Fax: +49 (0) 7125 940 401

Email: [tooling@de.sika.com](mailto:tooling@de.sika.com)

Internet: [www.sika.com](http://www.sika.com)

