

Biresin® RG53 FR Low pressure RIM-system, flame retardant

Areas of Application

- Manufacture of housings and coverings
- Manufacture of thin walled mouldings with complex structure
- Manufacture of flame retardant parts

Product Benefits

- Flame retardant V-0 according UL 94 at 3 mm thickness
- Classification of flammability according to EN DIN 5510-2 S4, ST2 and SR2
- Flammability according to appendix IV EU Directive R 95/28/EC at 3 mm thickness
- Fast curing with good flowability
- Short demoulding time
- Simulation of ABS with good impact resistance

Description

- Basis Two component PUR system
- Component A **Biresin® RG53 FR**, polyol, beige and black
- Component B **Biresin® U5**, MDI-based isocyanate, brown

Processing Data		Component A	Component B
Individual components		Biresin® RG53 FR	Biresin® U5
Viscosity, 25°C	mPa.s	~ 3,500	~ 110
Density	g/cm³	1.20	1.23
Mixing ratio A : B	in parts by weight	100	54
Mixing ratio A : B	in parts by volume	100	52
		Mixture	
Potlife, RT	s	~ 75	
Demoulding time, RT, dependent on thickness	min	> 10	
Curing time, RT	d	~ 1	

Physical Data (approx. values)

Biresin® RG53 FR (A)	with component B	Biresin® U5
Density	ISO 1183 g/cm³	1.27
Shore hardness	ISO 868 -	D 84
E-Modulus	ISO 178 MPa	2,200
Flexural strength	ISO 178 MPa	70
Tensile strength	ISO 527 MPa	45
Elongation at break	ISO 527 %	5
Impact resistance	ISO 179 kJ/m²	35
Heat distortion temperature	ISO 75B °C	110*

* values after post curing: 4 h / 80°C + 2 h / 120°C

Packaging

Individual components	Biresin® RG53 FR (A) beige and black Biresin® U5 (B)	200 kg; 25 kg net 250 kg; 20 kg; 5 kg net
-----------------------	---	--

Processing

- The material and processing temperature must be from 18 to 25°C, if necessary to 40°C; the mould temperature at least 20°C up to max. 60°C.
- Component A must be stirred thoroughly before use.
- For processing a two-component dosage mixing machine is necessary which conforms to reactivity of resin system and volume of casting parts.
- Machine vessel for component A must have a mixing unit and heating.
- Machine vessel for component B must be moisture tight, e. g. by installation of a silicagel filter.
- The resin and hardener components are to be mixed thoroughly and poured immediately into previously released moulds (e.g. with Sika® Liquid Wax-815 resp. Sika® Pasty Wax-818; for more information see product data sheet).
- Improved thermal stability of the demoulded mouldings can be obtained by post-curing.

Storage

- Minimum shelf life is 12 month under room conditions (18 - 25°C), when stored in original un-opened containers.
- Containers must be closed tightly immediately after use to prevent moisture ingress. The residual material needs to be used up as soon as possible.

Health and Safety Information

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety related data.

Disposal considerations

Product Recommendations: Must be disposed of in a special waste disposal unit in accordance with the corresponding regulations.

Packaging Recommendations: Completely emptied packagings can be given for recycling. Packaging that cannot be cleaned should be disposed of as product waste.

Value Bases

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

Legal Notice

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Further information available at:

Sika Deutschland GmbH

Subsidiary Bad Urach

Stuttgarter Str. 139

D - 72574 Bad Urach

Germany

Tel: +49 (0) 7125 940 492

Fax: +49 (0) 7125 940 401

Email: tooling@de.sika.com

Internet: www.sika.com



Results of Technical Fire Safety Testing of Biresin RG53 FR

- **Testing according to DIN 54837 (12/2009)** – Testing of materials, small parts, components for rail vehicles, determination of burning behaviour using a gas burner
Assessment according to DIN 5510, Part 2 (05/2009) on 4 mm samples
Flammability Class: S4
Smoke Development Class SR2
Capacity to form drops: Class ST2
- **Testing according to DIN 75200, ISO 3795**
Determination of the burning behaviour of materials of vehicle interiors with assessment of the maximum burning speed according to FMVSS 302:
Maximum value of the burning rate: 0 mm/min (2.8 mm sample thickness)
- **Testing according to Appendix IV EU Regulation 95/28/EG :**
Maximum value of the burning rate: 0 mm/min (3 mm sample thickness)
- **Burning behaviour according to UL94 (V):** Rated V-0 (3mm sample thickness)

Further information available at:

Sika Deutschland GmbH
Subsidiary Bad Urach
Stuttgarter Str. 139
D - 72574 Bad Urach
Germany

Tel: +49 (0) 7125 940 492
Fax: +49 (0) 7125 940 401
Email: tooling@de.sika.com
Internet: www.sika.com



BUILDING TRUST

