

DESCRIPTION

Semi-structural bonding : car body elements, numerous bonding in shipyard industry, bonding of glasses and thermoplastic elements

PROPERTIES

- 2 component room temperature cure polyurethane adhesive
- Non sagging paste product suitable for vertical applications and to fill irregular joints
- Fast setting product adapted to reduce assembly time
- Excellent vibrations, impacts and noise damping
- Excellent behaviour at low temperatures
- High elongation material (300%), product adapted to assemblies involving dissimilar materials
- Excellent mechanical performances and ageing
- Excellent strength to dynamic loads (vibrations and impacts)
- Product adapted to stringent ageing and aggressive environments

PHYSICAL PROPERTIES				
Composition	POLYOL	ISOCYANATE	Mix	Method
Mix ratio by weight	100	77		
Mix ratio by volume at 25°C	100	100		
Colour	Black	Light Amber	Black	
Viscosity at 25°C, Pa.s	Thixotropic paste -	28 – 36 (AKP)	Thixotropic paste -	LT-001
Density at 25°C (AKP)	1.48	1.10	-	LT-020
Density of cured product at 23°C	-	-	1.29	ISO 2781
Pot life at 23°C on 50 g, min (AKP)	-	-	5 - 5'30	LT-002-B
Open time on 7 mm bead at 23°C, min	-	-	4	LT-006-B

(AKP): Axson Key Properties. These values are enclosed in Certificate Of Analysis.

MECHANICAL PROPERTIES

Hardness, Shore A* (AKP)	75	LT-022
Tensile strength, MPa **	7	ISO 37
Elongation at break, % **	300	
Young Modulus, MPa **	8	
Recommended application temperature, °C	15 - 25	-
Working temperature, °C ***	-40 to 120	LT-006-B

*cured 2H at 80°C, measured at 1 second.

**cured 16H at 70°C.

*** Working temperature is defined as the temperature at which product keeps 80% of its initial Lap Shear Strength after 1000 hours ageing at this temperature, value on Aluminium, measured at 23°C.

HANDLING TIME

Handling time			
At 23°C	60	min	LT-006-B
At 40°C	30		
At 60°C	10		

Handling time is defined as the time needed to obtain Lap Shear Strength on Aluminum at 23°C, of 1MPa.

MECHANICAL PROPERTIES ON ASSEMBLIES (Cured 16H at 70°C)


Lap Shear Strength at 23°C				
Aluminium 2017A sandblasted		12 CF	MPa	LT-006-B
	After wet cataplasm 7 days at 70°C/100% RH	3 AF		
	After 15 cycles D3*	6.5 AF		
Stainless Steel 304 sandblasted		11 CF		
	After wet cataplasm 7 days at 70°C/100% RH	2.5 AF		
Electro galvanised Steel sandblasted		8 AF		
Electro galvanised Steel Acetone wipe		7 AF		
ABS Sanded + Isopropanol		4 SF		
PC Isopropanol wipe		5 SF		
PVC Sanded + Isopropanol		5 SF		
PMMA Sanded + Isopropanol		4 SF		
PA6E Sanded + Isopropanol		3 SCF		
GFR Polyester Isopropanol wipe		6 CF/DF 20%		
GFR Epoxy Isopropanol wipe		9 CF		

CF: Cohesive Failure, AF: Adhesive Failure, SCF: Special Cohesive Failure, SF: Substrate Failure, DF: Delamination Failure, according to EN ISO 10365 Standard.

*Cycle D3: exposition cycle in the heat, in the cold and in the humidity according to ISO 9142 standard.

Floating roller Peel Strength at 23°C				
Aluminum 2017A sandblasted		9	KN/m	ISO 4578

Lap Shear Strength on Aluminium versus Temperature



EQUIPMENT

ADEKIT A 252 is packaged in 50 ml and 400 ml cartridges and requires a manual or pneumatic gun. Please consult our technical department for applications needing a machine.

SUBSTRATE PREPARATION

The item to be bonded must be free of all dirt, oil or other foreign matter. A clean, dry surface is a must. Consult our Technical Support and refer to the technical data sheet about surface preparations to choose adapted degreaser or cleaner

HANDLING PRECAUTIONS

Normal health and safety precautions should be observed when handling these products :

- ensure good ventilation
- wear gloves and safety glasses
- wear waterproof clothes

For further information, please consult the product safety data sheet.



BUILDING TRUST



ADEKIT A 252

**THIXOTROPIC POLYURETHANE ADHESIVE
FOR FLEXIBLE BONDING**

STORAGE CONDITIONS

Shelf life of ADEKIT A 252 is **9 months** stored in its original unopened packaging at a temperature between +15°C and +25°C.

PACKAGING

A252 / 50ml	Box of 12 cartridges
A252 / 400ml	Box of 12 cartridges

GUARANTEE

The information contained in this technical data sheet result from research and tests conducted in our Laboratories under precise conditions. It is the responsibility of the user to determine the suitability of AXSON products, under their own conditions before commencing with the proposed application. AXSON guarantee the conformity of their products with their specifications but cannot guarantee the compatibility of a product with any particular application. AXSON disclaim all responsibility for damage from any incident which results from the use of these products. The responsibility of AXSON is strictly limited to reimbursement or replacement of products which do not comply with the published specifications.

AXSON TECHNOLOGIES
 Head Office France
 +33 1 34 40 34 60
axson@axson.fr
 axson.fr

GERMANY
 +49 60 74 40 71 10
verkauf@axson.de
 axson.de

ITALY
 +39 02 96 70 23 36
axson@axson.it
 axson.it

SPAIN & PORTUGAL
 +34 93 225 16 20
axson@axson.es
 axson.es

U.K.
 +44 1 638 66 00 62
sales@axson.co.uk
 axson.com

SLOVAKIA
 +421 37 642 25 26
office@axson-ce.sk
 axson-ce.sk

NORTH AMERICA
 +1 517 663 8191
info@axsontech.us
 axsontech.us

MEXICO
 +52 55 52 64 49 22
axson@prodigy.net.mx
 axson.com.mx

JAPAN
 +81 564 26 25 91
sales@axson.jp
 axson.jp

CHINA
 +86 21 58 68 30 37
china@axson.cn
 axson.cn

INDIA
 +91 20 25560710
info.india@axson.com
 axson.com

MIDDLE EAST
 +971 7 2432227
info.middleeast@axson.com
 axson.com