



BUILDING TRUST



ADEKIT A140-1

ADEKIT H 9940-1

STRUCTURAL EPOXY ADHESIVE
HIGH PERFORMANCES

Temporary Technical Data Sheet

DESCRIPTION

Bonding of car body, bonding metallic structures (racing vehicles, aeronautics), bonding inserts and composite structures

PROPERTIES

- 2 component high performance room temperature cured epoxy adhesive
- Non sagging paste product suitable for vertical applications and to fill irregular joints
- Excellent mechanical and thermal performances up to 130°C
- Excellent strength to dynamic loads (vibrations and impacts)
- Product adapted to stringent ageing and aggressive environments

PHYSICAL PROPERTIES				
Composition	RESIN	HARDENER	MIX	Method
Mix ratio by weight	100	90		
Mix ratio by volume at 25°C	100	100		
Colour	Beige (BG) Black (BK)	Beige	Beige (BG) Black (BK)	
Viscosity at 25°C, Pa.s (AKP)	950	NA	NA	LT-054 / 0.1 s⁻¹
Density at 25°C (AKP)	1.38	1.22	-	LT-020
Density of mixed product at 23°C	-	-	1.30	ISO 2781
Pot life at 23°C on 100g, min (AKP)	-	-	25	LT-002
Open Time on 7 mm bead at 23°C, min	-	-	40	LT-006-B

(AKP): Axson Key Properties. These values are enclosed in Certificate Of Analysis.

MECHANICAL PROPERTIES

Hardness, Shore D*	80	ISO 868
Tensile strength, MPa *	30	ISO 527-2
Elongation at break, % *	4	
Young Modulus, MPa *	2500	
Recommended application temperature, °C	15 - 30	-
Working temperature, °C **	-40 to 130	LT-006-B

*cured 16H at 70°C

** Working temperature is defined as the temperature at which product keeps 80% of its initial Lap Shear Strength after 1000 hours ageing at this temperature, value on Aluminium, measured at 23°C.

Page 1/4- TDS18F0019 – June 15th, 2018

AXSON FRANCE - SikaAxson
Head Office France
+33 1 34 40 34 60
axson@axson.com
www.sikaaxson.com

GERMANY
+49 (0)7125 940 492
tooling@de.sika.com
www.sikaaxson.de

ITALY
+39 02 96 70 23 36
axson@axson.it
axson.it

SPAIN & PORTUGAL
+34 93 225 16 20
spain@axson.com
axson.es

U.K.
+44 1 638 66 00 62
sales.uk@axson.com
axson.com

SLOVAKIA
+421 37 642 25 26
axson.sk@axson.com
axson-ce.sk

USA
+1 248 588 2270
axsonmh@axson.com
axson-na.com

MEXICO
+52 55 52 64 49 22
marketing@axson.com.mx
axson.com.mx

JAPAN
+81 564 26 25 91
sales.japan@axson.com
axson.jp

CHINA
+86 21 58 68 30 37
marketing.china@axson.com
axson.cn

INDIA
+91 20 25560710
info.india@axson.com
axson.com



BUILDING TRUST



ADEKIT A140-1

ADEKIT H 9940-1

STRUCTURAL EPOXY ADHESIVE
HIGH PERFORMANCES

Temporary Technical Data Sheet

HANDLING TIME

At 23°C	4h	LT-006-B
At 40°C	1h30	
At 60°C	30 min	

Handling time is defined as the time needed to obtain Lap Shear Strength on Aluminum at 23°C, of 1MPa.

MECHANICAL PROPERTIES ON ASSEMBLIES (Cured 16H at 70°C)

Lap Shear Strength at 23°C				
Aluminium 2017A sandblasted	Initial	20 CF	MPa	LT-006-B
	After wet cataplasm 7days 70°C/100% RH	16 CF		
	After 21 cycles D3**	16 CF		
Stainless Steel 304 sandblasted	23 CF			
Electro galvanised Steel sandblasted	21 CF			
Electro galvanised Steel Acetone wipe	20 CF			
ABS Sanded + Isopropanol	5 SF			
PC Sanded+Isopro.+ Plastic primer*	2 AF			
PVC Sanded + Isopropanol	5 SF			
PMMA Sanded + Isopro.+Plastic primer*	3 AF			
PAGE Sanded + Isopropanol	4.5 SF/AF			

CF: Cohesive Failure, AF: Adhesive Failure, SCF: Special Cohesive Failure, SF: Substrate Failure
DF: Delamination Failure, according to EN ISO 10365 Standard.

*Plastics sanded, Isopropanol wiped and coated with AXSON Plastic Primer.

**Cycle D3: exposition cycle in the heat, in the cold and in the humidity according to ISO 9142 standard.

Floating roller Peel Strength at 23°C				
Aluminum 2017A sandblasted		6 CF	KN/m	ISO 4578




BUILDING TRUST



ADEKIT A140-1 ADEKIT H 9940-1

STRUCTURAL EPOXY ADHESIVE
HIGH PERFORMANCES

Temporary Technical Data Sheet



EQUIPMENT: ADEKIT A140-1 is packaged in 50 ml and 400 ml cartridges and requires a manual or pneumatic gun. Please consult our technical department for applications needing a machine.

SUBSTRATE PREPARATION

The item to be bonded must be free of all dirt, oil or other foreign matter. A clean, dry surface is a must. Consult our Technical Support and refer to the technical data sheet about surface preparations to choose adapted degreaser or cleaner

HANDLING PRECAUTIONS

Normal health and safety precautions should be observed when handling these products :

- ensure good ventilation
- wear gloves and safety glasses
- wear waterproof clothes

For further information, please consult the product safety data sheet.

AXSON FRANCE - SikaAxson
 Head Office France
 +33 1 34 40 34 60
 axson@axson.com
 www.sikaaxson.com

GERMANY
 +49 (0)7125 940 492
tooling@de.sika.com
www.sikaaxson.de

ITALY
 +39 02 96 70 23 36
axson@axson.it
 axson.it

SPAIN & PORTUGAL
 +34 93 225 16 20
spain@axson.com
 axson.es

U.K.
 +44 1 638 66 00 62
sales.uk@axson.com
 axson.com

SLOVAKIA
 +421 37 642 25 26
axson.sk@axson.com
 axson-ce.sk

USA
 +1 248 588 2270
axsonmh@axson.com
 axson-na.com

MEXICO
 +52 55 52 64 49 22
marketing@axson.com.mx
 axson.com.mx

JAPAN
 +81 564 26 25 91
sales.japan@axson.com
 axson.jp

CHINA
 +86 21 58 68 30 37
marketing.china@axson.com
 axson.cn

INDIA
 +91 20 25560710
info.india@axson.com
 axson.com



BUILDING TRUST



ADEKIT A140-1 ADEKIT H 9940-1

**STRUCTURAL EPOXY ADHESIVE
HIGH PERFORMANCES**

Temporary Technical Data Sheet

STORAGE CONDITIONS

Shelf life of ADEKIT A140-1 and of ADEKIT H 9940 POLYOL / H9940-1 ISOCYANTE is **12 months**, stored in its original unopened packaging at temperature between +15°C and +25°C.

PACKAGING

A140-1 / 50ml	Box of 12 cartridges
A140-1 / 400ml	Box of 12 cartridges
H9940 Resin & H9940-1 Hardener	Please consult our Sales Department

GUARANTEE

The information contained in this technical data sheet result from research and tests conducted in our Laboratories under precise conditions. It is the responsibility of the user to determine the suitability of AXSON products, under their own conditions before commencing with the proposed application. AXSON guarantee the conformity of their products with their specifications but cannot guarantee the compatibility of a product with any particular application. AXSON disclaim all responsibility for damage from any incident which results from the use of these products. The responsibility of AXSON is strictly limited to reimbursement or replacement of products which do not comply with the published specifications.

Page 4/4- TDS18F0019 – June 15th, 2018

AXSON FRANCE - SikaAxson
Head Office France
 +33 1 34 40 34 60
 axson@axson.com
 www.sikaaxson.com

GERMANY
 +49 (0)7125 940 492
tooling@de.sika.com
www.sikaaxson.de

ITALY
 +39 02 96 70 23 36
axson@axson.it
 axson.it

SPAIN & PORTUGAL
 +34 93 225 16 20
spain@axson.com
 axson.es

U.K.
 +44 1 638 66 00 62
sales.uk@axson.com
 axson.com

SLOVAKIA
 +421 37 642 25 26
axson.sk@axson.com
 axson-ce.sk

USA
 +1 248 588 2270
axsonmh@axson.com
 axson-na.com

MEXICO
 +52 55 52 64 49 22
marketing@axson.com.mx
 axson.com.mx

JAPAN
 +81 564 26 25 91
sales.japan@axson.com
 axson.jp

CHINA
 +86 21 58 68 30 37
marketing.china@axson.com
 axson.cn

INDIA
 +91 20 25560710
info.india@axson.com
 axson.com