

PRODUCT DATA SHEET

SikaBiresin® F155 / SikaBiresin® F150

UNFILLED FASTCAST RESIN FOR PRODUCTION OF CLIMBING HOLDS – POT LIFE 7'

APPLICATIONS

- Production of wear resistant and impact resistant climbing holds

MAIN PROPERTIES

- High abrasion resistance
- High impact resistance
- Quick setting
- Easy processing
- Can be easily pigmented with SikaBiresin® Colour Paste

DESCRIPTION

Basis	Two component polyurethane system
Component A	SikaBiresin® F155 , polyol, unfilled, off white
Component B	SikaBiresin® F150 , MDI-based isocyanate, unfilled, yellowish

PHYSICAL PROPERTIES

Components		Polyol (A)	Isocyanate (B)
		SikaBiresin® F155	SikaBiresin® F150
Viscosity, 25 °C	mPa.s	~ 650	~ 500
Density, 25 °C		~ 1.03	~ 1.21
Mixing ratio	in parts by weight	100	100
		Mixture	
Colour		Off white	
Viscosity, 25 °C	mPa.s	~ 600	
Pot life, 100g, 25°C	min	~ 7	
Demoulding time, 25°C	min	~ 90-120	

MECHANICAL PROPERTIES

(approx. values after 16h @ 70°C)

Density, 25 °C	ISO 1183	-	1.19
Shore hardness	ISO 868	-	D 81
Tensile modulus	ISO 527	MPa	2200
Tensile strength	ISO 527	MPa	53
Elongation at maximum strength	ISO 527	%	6
Flexural modulus	ISO 178	MPa	2100
Flexural strength	ISO 178	MPa	87
Impact strength (CHARPY) <i>Unnotched specimens</i>	ISO 179	kJ/m ²	78
Abrasion resistance	ISO 4649	mm ³	260

THERMAL AND SPECIFIC PROPERTIES

(approx. values after 16h @ 70°C)

Heat distortion temperature	ISO 75B	°C	50
Glass transition temperature	TMA Mettler	°C	64

PACKAGING UNITS

- | | |
|--|----------------|
| ■ Polyol (A), SikaBiresin® F155 | 200 kg / 20 kg |
| ■ Isocyanate (B), SikaBiresin® F150 | 225 kg / 20 kg |

PROCESSING DATA

- The material, processing and mould temperature should be at least 18 – 25 °C.
- Pay attention to dry conditions and dry mould surfaces while processing.
- If mould surface is porous it must be sealed prior applying release agent
- Silicone elastomer ESSIL 222 is recommended as mold to cast SikaBiresin® F155/F150.
- If using other molds than silicones recommended release agents are wax based. For more information and recommendation see Product Data Sheets of Sika release agents or contact local technical assistance.
- To pigment in various colors SikaBiresin® Colour Paste are highly effective and please refer to their specific Product Data Sheet for proper handling.
- Both components must be shaken or stirred well before use.
- Both components have to be mixed thoroughly with a spatula or low-rpm stirrer according to mixing ratio and poured immediately into the mould starting from the deepest point.
- Further post curing of the demoulded part can improve the final mechanical properties.
- Depending on the geometry and weight of the part, it is recommended to use a conformer while post curing.
- For cleaning the final part from release agent residues, we recommend Sika® Reinigungsmittel-5. Before use of other cleaners, compatibility must be tested.

STORAGE CONDITIONS

PRODUCT DATA SHEET
SikaBiresin® F155 / SikaBiresin® F150
December 2022, Version 01
Sika Advanced Resins

Shelf life	▪ Polyol (A), SikaBiresin® F155	12 months
	▪ Isocyanate (B), SikaBiresin® F150	9 months
Storage temperature	▪ Polyol (A), SikaBiresin® F155	15 – 25 °C
	▪ Isocyanate (B), SikaBiresin® F150	15 – 25 °C
Crystallization	<ul style="list-style-type: none"> ▪ After prolonged storage at low temperature crystallization of Isocyanate (B) and Polyol (A) may occur. ▪ This is easily removed by warming up for enough time to a maximum of 60 °C. ▪ Allow to cool to requested processing temperature before use. 	
Opened packagings	<ul style="list-style-type: none"> ▪ Containers must be closed tightly immediately after use to prevent moisture ingress. ▪ The residual material needs to be used up as soon as possible. 	

FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Advanced Resins. Copies of the following publications are available on request: Safety Data Sheets

BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

HEALTH AND SAFETY INFORMATION

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTICE

The information, and, in particular, the recommendations relating to the application and enduse of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Contact

SIKA DEUTSCHLAND GMBH

Business Unit Industry
Stuttgarter Straße 139
72574 Bad Urach
Phone: +49 7125 940-7692
E-Mail: industry@de.sika.com
Website: www.sika.de

SIKA AUTOMOTIVE FRANCE S.A.S.

ZI des Béthunes - 15, Rue de l'Equerre
95310 Saint-Ouen-l'Aumône
CS 40444
95005 Cergy Pontoise Cedex - FRANCE
Phone: +33 1 34 40 34 60
Fax: +33 1 34 21 97 87
E-Mail: advanced.resins@fr.sika.com
Website: www.sikaadvancedresins.fr

Sika S.A.U.

Carretera de Madrid a Irún – km 14.5
P.I. Congost 28108 Alcobendas (Madrid) - SPAIN
Phone: +34 93 225 16 20
E-Mail: sar-sales@es.sika.com
Website: www.sikaadvancedresins.es

Sika Italia S.p.A.

Via Luigi Einaudi 6
20068 Peschiera Borromeo (MI) - Italy
Phone: +39 02 54778111
Fax: +39 02 54778 119
E-Mail: info@sika.it
Website: www.sika.it

Sika Limited

Head Office, Watchmead – Welwyn
Garden City – AL7 1BQ – United Kingdom
Phone: +44 1707 394444
E-Mail: industry-sales@uk.sika.com
Website: www.gbr.sika.com

SIKA AUTOMOTIVE SLOVAKIA S.R.O.

Tovarenska 49
953 01 Zlate Moravce - SLOVAKIA
Phone: +421 2 5727 29 33
Fax: +421 37 3000 087
E-Mail: SikaAdvancedResins@sk.sika.com
Website: www.sikaadvancedresins.com

Sika Industry – Tooling, Resins and Marine

30800 Stephenson Highway
Madison Heights, Michigan 48071 - USA
Phone: +1 248 588 2270
Fax: +1 248 616 7452
E-Mail: advanced.resins@us.sika.com
Website: www.sikaindustry.com

SIKA AUTOMOTIVE EATON RAPIDS, INC.

1611 Hults Drive
Eaton Rapids, Michigan 48827 - USA
Phone: +1 517 663 81 91
Fax: +1 517 663 05 23
E-Mail: advanced.resins@us.sika.com
Website: www.sikaadvancedresins.us

SIKA MEXICANA SA de CV

Av. Gustavo Baz #309 Centrum Park
54060 Tlanepantla Estado de MEXICO
Phone: +52 442 238 5800
E-Mail: roman.octavio@mx.sika.com

SIKA AUTOMOTIVE SHANGHAI CO. LTD.

N°53 Tai Gu Road
Wai Gao Qiao
Free Trade Zone, Pudong
200131 Shanghai - CHINA
Phone: +86 21 58 68 30 37
Fax: +86 21 58 68 26 01
E-Mail: industry@cn.sika.com
Website: www.sika.cn

Sika Ltd.

10 F, Shinagawa Intercity Tower B.
2-15-2 Konan, Minato-ku
Tokyo 108-6110 - JAPAN
Phone: +81 3 6433 2314
Fax: +81 3 6433 2102
E-Mail: advanced-resins@jp.sika.com
Website: www.jpn.sika.com

SIKA INDIA PVT LTD,

Plot No. Pap-V-90/1,
Chakan Industrial Area,
Phase-II, Vasuli, Khed, PUNE,
Maharashtra – 410501
E-Mail: info.india@in.sika.com